

## PROCESSING BLACK & WHITE FILM

STAGE	INSTRUCTIONS
<b>DEVELOPER</b> Mix 2oz of Developer with 18oz of water.	Tap once. Constant agitation for first minute. Then 5 seconds every 30 seconds after first minute. 68° 10 1/2 minutes for HP5+      10 Minutes for Tri-X 70° 09 1/2 minutes for HP5+      09 Minutes for Tri-X
<b>WATER STOP BATH</b>	1 minute of constant agitation. Use plain water, check temperature.
<b>FIXER PREMIXED</b> (do not add water)	5 minutes: Agitate every other minute. Pour back into graduate. Bottle has premixed, test before using, otherwise see dilution chart.
<b>PREWASH</b>	Agitate for 30 seconds, pour out and repeat once. Use plain water, check temperature.
<b>FIXER REMOVER PREMIXED</b> (do not add water)	1 minute of constant agitation. Pour back into graduate. Bottle has premixed, discard if Yellow, otherwise see dilution chart.
<b>FINAL WASH</b>	Agitate for 1 minute, pour out and repeat 4 more times. Use plain water, check temperature.
<b>WETTING AGENT</b>	Dip into graduate for 1 Minute. No agitation. Premixed, do not dilute.

**NOTE: Fixer and Fixer Remover do not get poured down the drain.**